

DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"-

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 9, 2008

HEWLITT-PACKARD COMPANY 16399 West Bernardo Drive San Diego, CA 92127-1899

Reference: Laboratory Test Report

Lab Identification No. 5079 Invoice No. 17404 (Attached)

Dear Sirs:

One (1) scrim banner sample, identified as HP OPAQUE SCRIM Q 8675A, LOT 179161, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The results are as follows:

Specimen Number	After Flame Time		Char Length	
	Length	Width	Length	Width
1	4.0	0.0	3.7	3.8
2	6.0	6.0	3.9	3.8
3	6.0	4.0	4.1	3.2
4	0.0	3.0	3.7	3.7
5	0.0	0.0	3.5	3.4
Avq.	3.2	2.6		

The sample submitted, in its original state, meets the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.


Sincerely

Karon S. Matkins

KSM/mr Attachment

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAF PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.

DIVERSIFIED



TESTING LABORATORIES, INC.

"We Test Per Your Request" -

336 WEST FRONT STREET P.O. BOX 4004 **BURLINGTON, NORTH CAROLINA 27215** PHONE (336) 227-7710 • FAX (336) 227-1175 www.diversifiedtestinglabs.com

January 9, 2008

HEWLITT-PACKARD COMPANY 16399 West Bernardo Drive San Diego, CA 92127-1899

Reference: Laboratory Test Report

Lab Identification No. 5079 Invoice No. 17404 (Attached)

Dear Sirs:

One (1) scrim banner sample, identified as HP OPAQUE SCRIM Q 8675A, LOT 179161, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The sample was tested after 72 hours of leaching. The results are as follows:

Specimen Number	After Fl	After Flame Time		Char Length	
	Length	Width	Length	Width	
1	3.0	3.0	3.9	3.9	
2	0.0	6.0	4.2	4.4	
3	0.0	8.0	4.4	3.9	
4	0.0	0.0	3.7	4.1	
5	3.0	0.0	3.9	3.6	
Avg.	1.2	3.4			

The sample submitted, when tested after 72 hours of leaching, meets the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karbn S. Matkin

KSM/mr Attachment

DIVERSIFIED



TESTING LABORATORIES, INC.

-"We Test Per Your Request"-

336 WEST FRONT STREET P.O. BOX 4004 BURLINGTON, NORTH CAROLINA 27215 PHONE (336) 227-7710 • FAX (336) 227-1175 www.diversifiedtestinglabs.com

January 9, 2008

HEWLITT-PACKARD COMPANY 16399 West Bernardo Drive San Diego, CA 92127-1899

Reference: Laboratory Test Report

Lab Identification No. 5079 Invoice No. 17404 (Attached)

Dear Sirs:

One (1) scrim banner sample, identified as HP OPAQUE SCRIM Q 8675A, LOT 179161, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The sample was tested after 100 hours of accelerated weathering. The results are as follows:

Specimen Number	r After Fla	After Flame Time		Char Length	
	Length	Width	Length	Width	
1	0.0	0.0	4.1	4.2	
2	0.0	0.0	3.7	3.8	
3	0.0	0.0	3.6	4.1	
4	0.0	0.0	3.0	3.6	
5	0.0	0.0	3.8	4.3	
Avg.	0.0	0.0			

The sample submitted, when tested after 100 hours accelerated weathering, meets the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

on S. Matkin

KSM/mr Attachment

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUS RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAL PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NO BE USED IN ADVERTISING TO THE GENERAL PUBLIC.